



## Uni- Finish

Uni-Finish is modified gypsum finishing plaster for use on wide range of backgrounds. It provides a smooth and high quality surface to internal walls and ceilings.

- Specially formulated with additive for strong surface hardness, adhesion and brilliant appearance
- It is paste-like and easy to apply
- Special grain size distribution gives very smooth surface

# Uni-Finish



Water Resistant



Super White



Very Smooth Surface



Strong Adhesion

### Application

- Clean dust and any substance preventing adherence on the surface
- Put some water in a clean bowl. Sprinkle Uni-FINISH until it covers the water surface. Wait 2 minutes, and then mix the mortar until obtaining homogeneous mixture
- Use plaster trowel and steel spatula for the application. Scrape off the residues after setting

### Recommendation

- Do not mix UNI-FINISH with any other material
- Optimal water / plaster ratio is 6.5-7 liter water for every 10 kg of Uni-FINISH
- Do not add water or plaster to the mortar after mixing
- Use low speed mechanical mixer
- Apply thickness at min of 1 mm and max 3 mm
- Do not use at temperature below +5 °C
- Use internally only

### Storage condition

- Store in dry place at no more than 20 layers
- Use within one year after the date of production. Inappropriate and too-long storage may deteriorate the physical properties of Uni-Finish

### Technical Specifications

Water / Plaster ratio	6.5-7 liter water to 10 kg (UNI-FINISH)
Workability	60 minutes
Final Setting Time	130 minutes
Consumption	1kg/m <sup>2</sup> for each 1 mm thickness
Compressive Strength (minimum)	3.5 MPa
Bag net weight	25kg ± 2%
Standard	EN 13279-1-C6/20/2

## يوني - فنش

يوني - فنش هو معجون للجدران معالج ومتخصص للإستخدام الداخلي ، ويعمل كطبقة معجون أساس قبل الدهان . يعطي سطح صلب وناعم وذو جودة عالية للجدران والأسقف الداخلية.

- تمت معالجته عن طريق إضافات خاصة ليعطي السطح صلابة وقوة إتصاق كبيرة مع مظهر جميل
- معجون فائق الجودة وسهل التطبيق
- توزيع متساوي لحجم الحبيبات للحصول على أسطح ناعمة جداً



## يوني - فنش



التصاق قوي



سطح ناعم جداً



ناعم البياض



مقاوم للمياه



## الإرشادات

- لا تخلط يوني - فنش مع مادة أخرى
- نسبة الخلط القياسية ٦,٥ - ٧ لتر ماء لكل ١٠ كج من يوني - فنش
- لا تضيف الماء للخلطة بعد عملية الخلط
- إستخدم الخلاط بسرعة منخفضة
- سمك المعجون يجب أن لا يقل عن ١ ملم ولا يزيد عن ٣ ملم
- لا تقم بتنفيذ المعجون في وقت تكون فيه درجة حرارة الجو أقل من ٥ درجات مئوية
- للإستخدام الداخلي فقط

## شروط التخزين

- قم بالتخزين في مكان جاف بما لا يزيد عن ٢٠ رصة
- إستخدم يوني فنش خلال سنة من تاريخ الإنتاج .
- التخزين الخاطئ أو التخزين طويل الأمد قد يضر بالخصائص الفيزيائية للمنتج

## التطبيق

- نظف الجدار من الغبار أو أي مادة تمنع الإلتصاق
- ضع بعض الماء في وعاء ثم رش بوردرة يوني- فنش في وعاء حتى تغطي سطح الماء
- انتظر دقيقتين ثم اخلط حتى تحصل على عجينة متجانسة
- إستخدم سكين معجون لتنفيذ يوني- فنش على الجدران
- أكشط الزيادات بعد التصلب

## المواصفات الفنية

نسبة الماء / البوردرة	٦,٥ - ٧ لتر لكل ١٠ كج من يوني- فنش
زمن العمل	٦٠ دقيقة
وقت التصلب	١٣٠ دقيقة
الإستهلاك	١ كج لكل ٢ م <sup>٢</sup> بسماكة ١ ملم
قوة الضغط	٣,٥ ميجا باسكال
وزن الكيس	٢٥ كج ± ٢%
مواصفات	EN ١٣٢٧٩-١-٢٠٠٢ / C ٢ / ٢



لافارج هولسيم

شركة الجبس العالمية المحدودة

إنتاج شركة الجبس العالمية المحدودة  
بنيغ الصناعية - المملكة العربية السعوديةهاتف : ٧٢ - ٦٦٢ (١٢) ٩٦٦ +  
فاكس : ٦٩٨٦٩٦٥ (١٢) ٩٦٦ +

مصنع بنيغ الصناعية

هاتف : ٣٢٥٤٨٨٨ (١٤) ٩٦٦ +  
فاكس : ٣٢٥٤٩٩٩ (١٤) ٩٦٦ +

إحداثيات المصنع E38.255 N24.015

Info@global-gypsum.com

www.global-gypsum.com

صنع في المملكة العربية السعودية

